



BW-936

All Purpose SOY BLEND

BW-936 is an all-natural premium soy wax blend used for single pour, scented pillars, melts/tarts, and container candles. This wax blend is offered in slabs, pastilles and bulk format, is off-white, with a good mold release and a smooth finish.



PROPERTIES

Melting Point (D-938): Typical: 130°F

Color (ASTM): Typical: L1.0 (Off-White)

Needle Penetration (D-1321):

0.1mm @ 77°F / 25°C

Typical: 30

BENEFITS

- Single pour
- Pre-Blended, no additives required

- Smooth finish
- Accepts dyes and colorants well

Containers:

- Good jar adhesion
- Will not creep/slump at temperatures up to 100°F
- Bloom resistant

Pillars & Melts/Tarts:

- Good mold release
- Even burn
- High fragrance load

INSTRUCTIONS

Pillars:

- 1 **Fragrance Addition: Up to 10%**
- 2 **Pour Temp: 160°F - 170°F**
- 3 **Pour process may include recapping**

Containers:

- 1 **No jar preheating required**
- 2 **Fragrance Addition: 7% - 9%**
- 3 **Pour Temp: 160°F - 170°F**

Melts/Tarts:

- 1 **Fragrance Addition: Up to 15%**
- 2 **Pour Temp: 160°F - 170°F**

- Evaluate wicks for each fragrance/dye combination
- Results obtained from using 24-ounce aluminum pillar molds and flat braid 27 ply wicks
- Addition of fragrance/dyes to candle blends can change wicking properties, often requiring adjustment of wick size to obtain optimal burning

- Evaluate wicks for each fragrance/dye combination
- Results obtained from using 12-ounce apothecary jars and HTP-1212 pre-tabbed wicks
- Addition of fragrance/dyes to candle blends can change wicking properties, often requiring adjustment of wick size to obtain optimal burning

- Results obtained from using 3-ounce plastic clamshell molds

If you want more information or have any questions, please contact our Customer Service Team at: (920) 236-8080, or info@blendedwaxes.com

Blended Waxes
1512 S. Main St.
Oshkosh, WI 54902
920-236-8080
blendedwaxes.com

USA MADE



Follow us on social!



All waxes have been tested and performance evaluated by Blended Waxes, Inc. using best practices for the industry and are believed to be reproducible. There are many variables that cannot be accounted for in the performance of Blended Waxes, Inc. candle products that are described in this sales literature. These variables include, but are not limited to; mold size, container size, container composition, fragrance amount, fragrance type, dyes, colorings, wicks, pouring temperatures, environment, etc. There are no warranties, representations or conditions, expressed or implied, of any kind, including, but limited to, merchantability or ability to use products for particular purpose made by Blended Waxes, Inc. or its officers, employees or its affiliates in connection with the sale of waxes intended for use in candles or other industries. It is the purchaser's obligation to determine the suitability of the candle waxes in this sales literature for their intended purposes. Purchasers and users assume all liabilities and risk with their use of all the waxes in this sales literature. All candle waxes included in this sales literature should be handled in accordance to health, safety and compliance regulations. Please consult Blended Waxes, Inc. SDS prior to handling.