



BW-886

BEEHIVE WAX

Blended Waxes Beehive Wax, BW-886, is paraffin, microcrystalline wax blend used as an outer protective coating for wooden beehives.



PROPERTIES

Melting Point (D-938):

Typical: 140°F

Needle Penetration (D-1321):

0.1mm @ 77°F / 25°C

Typical: 20

0.1mm @ 100°F / 38°C

Typical: 80

BENEFITS

- Preserves the wood against environmental factors
- Protects the bees from disease
- Adheres to and coats the wood boards better than paraffin or microcrystalline wax alone
- FDA Status: Compliance with Federal Regulations 21 CFR-178.3710 and 172.886

INSTRUCTIONS

- 1 Heat container of wax to 160°F - 170°F
- 2 Dip box into wax and let it submerge for a few minutes so the wax can soak into the wood
- 3 Remove the boards and let wax drip off and solidify

- If boards are wet, moisture may seep out of wood while dipping. It is best to use dry wood.
- Before dipping, ensure boards are free of any dust and debris

If you want more information or have any questions, please contact our Customer Service Team at: 920-236-8080, or info@blendedwaxes.com

Blended Waxes
1512 S. Main St.
Oshkosh, WI 54902
920-236-8080
blendedwaxes.com

USA MADE



Follow us on social!



All waxes have been tested and performance evaluated by Blended Waxes, Inc. using best practices for the industry and are believed to be reproducible. There are many variables that cannot be accounted for in the performance of Blended Waxes, Inc. candle products that are described in this sales literature. These variables include, but are not limited to; mold size, container size, container composition, fragrance amount, fragrance type, dyes, colorings, wicks, pouring temperatures, environment, etc. There are no warranties, representations or conditions, expressed or implied, of any kind, including, but limited to, merchantability or ability to use products for particular purpose made by Blended Waxes, Inc. or its officers, employees or its affiliates in connection with the sale of waxes intended for use in candles or other industries. It is the purchaser's obligation to determine the suitability of the candle waxes in this sales literature for their intended purposes. Purchasers and users assume all liabilities and risk with their use of all the waxes in this sales literature. All candle waxes included in this sales literature should be handled in accordance to health, safety and compliance regulations. Please consult Blended Waxes, Inc. SDS prior to handling.